

MOTIP High temp

Ord.-no.: look at ordering information

Technical Information



Lacquer to treat surfaces, treated and untreated, which are exposed to very high temperatures. The lacquer is resistant to petrol, chemicals and weather influences. Deco Effect Heat Resistant Lacquer is available in 3 colours, black, silver and dark anthracite and is heat resistant to 800°C.

Quality & properties

- Excellent coverage
- Fast drying
- Heat resistant to 800°C

Physical & chemical data

- Vapour pressure:
 - ◊ 3500/20 bar
 - ◊ 5,7/20 bar
- Flash point:
 - ◊ n.a. °C
 - ◊ 23 °C
- Content:
 - ◊ 0.2398
 - ◊ 0.238
 - ◊ 0.032

How to use

- The surface should be clean, dry and free of grease. Slightly sand the surface (grain 600).
- The aerosol should have room temperature. Best processing temperature 15 to 25°C. Before use, shake the aerosol for 2 minutes and spray a sample. Distance to the surface to be treated approximately 25 to 30 centimetre.
- Apply the lacquer in several thin layers. Before applying the next layer, again shake the aerosol.
- After use, clean the valve (turn aerosol upside down and press the nozzle for approximately 5 seconds).
- The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.

Environmentally sound

European Aerosols is committed to apply formulations without restricted or critical ingredients and to achieve best possible performance. The caps and packagings are made of recyclable material.

Disposal

Only the completely emptied cans should be put into the recycling skip or appropriate container for reclaimable refuse. Cans which are not empty should be disposed off as "special refuse".

Marking/Labeling

All products made by European Aerosols comply with the actual labelling regulations according to Preparation Guideline 1999/45/EG. All aerosols correspond to TRGS 200 and TRG 300 as well as to aerosol guideline 75/324/EWG in the actually valid version.

For any further technical questions call our hotline +31 (0) 561 69 44 00 from Monday to Thursday from 9 h a.m. to 3 h p.m. or on Friday until 12 h p.m.

As of November 29, 2021 – This release replaces all eventually earlier issued versions.