

## MOTIP Polyester Putty (Profi)

Ord.-no.: 000056

### Technical Information



Universal two-component polyester putty to level irregularities in surfaces of steel, aluminium, wood, concrete and polyester. Polyester putty is elastic and very easy to sand. Polyester putty is re-sprayable with all lacquer systems and resistant to chemicals and the weather. Polyester putty can be applied in layers with a thickness up to 2 cm.

#### Quality & properties

- Ease of working
- Excellent adhesion on different surfaces
- Easy to sand
- Free of asbestos and silicone
- Resistant to weak acids and bases, propellants, solvents, water and de-icing salt

#### Physical & chemical data

- Base: Polyester resin
- Colourname: grey
- Content: 2,00 KG

#### How to use

- Before use, carefully read the directions on the packaging and act accordingly.
- Processing temperature 15 – 25°C.
- The surface should be clean, dry and free of grease. Remove loose old lacquer and rust and sand the surface.
- Take the requested portion of putty compound out of the can and mix it well with the corresponding quantity of hardener.
- Apply the mixed material in the desired layer thickness.
- After approx. 20-30 minutes the repaired spot can be drilled, sanded, sawed, rasped and painted.
- The drying time depends on the ambient temperature.
- After use, directly clean the tools used. Do not store the surplus material, mixed with harder, in the can.

#### Environmentally sound

European Aerosols is committed to apply formulations without restricted or critical ingredients and to achieve best possible performance. The caps and packagings are made of recyclable material.

#### Disposal

Only the completely emptied cans should be put into the recycling skip or appropriate container for reclaimable refuse. Cans which are not empty should be disposed off as "special refuse".

#### Marking/Labelling

All products made by European Aerosols comply with the actual labelling regulations according to Preparation Guideline 1999/45/EG. All aerosols correspond to TRGS 200 and TRG 300 as well as to aerosol guideline 75/324/EWG in the actually valid version.

For any further technical questions call our hotline +31 (0) 561 69 44 00 from Monday to Thursday from 9 h a.m. to 3 h p.m. or on Friday until 12 h p.m.

**As of August 17, 2022** – This release replaces all eventually earlier issued versions.