

MOTIP Polyester Fibre Putty (Profi)

Ord.-no.: 000084

Technical Information



Universal two-component polyester putty to level irregularities in surfaces of steel, aluminium, wood, concrete and polyester. Polyester putty is elastic and very easy to sand. Polyester putty is re-sprayable with all lacquer systems and resistant to chemicals and the weather. Polyester putty can be applied in layers with a thickness up to 2 cm.

Quality & properties

- Ease of working
- Easy to sand
- Very good adherence
- Resistant to weak acids and bases, propellants, solvents, water and de-icing salt
- Free of asbestos and silicone
- Short curing time

Physical & chemical data

- Base: Polyester resin with mineral fillers
- Colourname: grey
- Smell: Characteristic
- Degree of gloss: mat, 10 \pm 2
- Completely dry: 30 min
- Surfaces: Steel, aluminium, wood, concrete, polyester
- Minimum Working Temperature: 10
- Maximum Working Temperature: 25
- Relative density: 1.46 g/ml
- Addition of hardener: 2.5 %
- Content: 1,50 KG

How to use

- Before use, carefully read the directions on the packaging and act accordingly.
- The surface should be clean, dry and free of grease. Remove loose old lacquer and rust and sand the surface.
- Take the requested portion of putty compound out of the can and mix it well with the corresponding quantity of hardener.
- Apply the mixed material in the desired layer thickness.
- Clean tools immediately after use, if necessary with a nitro thinner. Do not return mixed material into the can.
- After approx. 20-30 minutes the repaired spot can be drilled, sanded, sawed, rasped and painted.
- The drying time depends on the ambient temperature.

Environmentally sound

European Aerosols is committed to apply formulations without restricted or critical ingredients and to achieve best possible performance. The caps and packagings are made of recyclable material.

Disposal

Only the completely emptied cans should be put into the recycling skip or appropriate container for reclaimable refuse. Cans which are not empty should be disposed off as "special refuse".

Marking/Labelling

All products made by European Aerosols comply with the actual labelling regulations according to Preparation Guideline 1999/45/EG. All aerosols correspond to TRGS 200 and TRG 300 as well as to aerosol guideline 75/324/EWG in the actually valid version.

For any further technical questions call our hotline +31 (0) 561 69 44 00 from Monday to Thursday from 9 h a.m. to 3 h p.m. or on Friday until 12 h p.m.

As of August 17, 2022 – This release replaces all eventually earlier issued versions.